

THERBAN[®] 3629

Product Description

A partially hydrogenated butadiene acrylonitrile copolymer designed primarily for applications requiring excellent resistance to heat, ozone and non polar hydrocarbon fluids. Special low RDB - type to increase crosslink density for high module and low compression set applications. While sulfur curing systems can be used for improved dynamic properties and adhesion to steel and textile reinforcing materials, peroxide/coagent systems are recommended. High molecular weight provides for capacity of high plasticizer and filler loads.

Supply Form

Bales

Raw Material Properties

Property	Nominal Value	Unit	Test Method
Mooney Viscosity ML (1+4) 100°C	87 ± 7	MU	ISO 289/ASTM D 1646
Acrylonitrile content	36 ± 1.5	wt %	ISO 24698-1
Residual double bonds	2.0 ± 0.5	%	IR Spectroscopy
Volatile matter	≤ 0.49	wt %	ISO 248/ASTM D 5668

Other Product Features

Property	Typical Value		
Specific gravity	0.96		
Total Ash	≤ 0.49	wt %	ISO 247/ASTM D 5667
Stabilizer	Non-staining		
Solubility	Soluble in MEK		
Color	Light brown		

THERBAN[®] 3629

Packaging	25 kg bales wrapped in blue PE-film strippable / dispersible (melting point of film = 85 - 110°C, Vicat softening point = 71°C, 0.08 mm thick) pallets of 20 bales (500kg)
Shelf life	36 months from date of production at temperatures not exceeding 35°C in dry conditions; exposure to light has to be avoided
Product Safety	Relevant safety data and references as well as the possibly necessary warning labels are to be found in the safety data sheet.

These raw material properties are typical and, unless specifically indicated otherwise, are not to be considered as delivery specification.

THERBAN[®] is a Registered Trademark of LANXESS Deutschland GmbH

This information and our technical advice – whether verbal, in writing or by way of trials – are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided – especially that contained in our safety data and technical information sheets – and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.

Issue number: ARL 01 / Date of issue: May 19, 2016 / Previous issue from LXS 07 January 01, 2010 / Information current as of date of issue. Please contact your ARLANXEO representative to determine if this publication has been revised.